

# AC 2101 CHOPPED FIBER TECHNICAL DATA SHEET

## FIBER PROPERTIES

	English		Metric		Test Method
Tensile Strength	610	ksi	4200	MPa	ISO 10618
Tensile Modulus	34,8	Msi	240	GPa	ISO 10618
Elongation	1.8	%	1,8	%	ISO 10618
Density	0,064	Ft-lbs/in <sup>3</sup>	1,76	kJ/m <sup>2</sup>	ISO 10119

## CHOPPED FIBER PROPERTIES

Chopped Fiber Properties					
Product Code	Applications	Fiber Lengths, mm	Typical Bulk Density (For 6mm cut lengths) (g/l)	Sizing Emulsion	Sizing content (%)
AC 2101	Thermoplastics (High Temperature) - PEEK, Amide, Imide.	6	500	Polyimide based	0,5 - 1,0

### DowAksa İleri Kompozit Malzemeler Sanayi LTD. ŞTİ.

**Head Office:** Miralay Şefik Bey Sok. Akhan No: 15 34437 Gümüşsuyu - İstanbul / TÜRKİYE  
T: +90(212) 251 45 00 • F: +90(212) 249 35 99

**Plant:** Denizçalı Köyü Yalova - İzmit Yolu Cad. No: 34  
77600 Yalova / TURKEY

T: +90 226 353 25 45

[www.dowaksa.com](http://www.dowaksa.com) • [cfsales@dowaksa.com](mailto:cfsales@dowaksa.com)