

AC 4101 CHOPPED FIBER TECHNICAL DATA SHEET

FIBER PROPERTIES

	English		Metric		Test Method
Tensile Strength	610	ksi	4200	MPa	ISO 10618
Tensile Modulus	34,8	Msi	240	GPa	ISO 10618
Elongation	1.8	%	1,8	%	ISO 10618
Density	0,064	Ft-lbs/in ³	1,76	kJ/m ²	ISO 10119

CHOPPED FIBER PROPERTIES

Chopped Fiber Properties					
Product Code	Applications	Fiber Lengths, mm	Typical Bulk Density (For 6mm cut lengths) (g/l)	Sizing Emulsion	Sizing content (%)
AC 4101	Thermoplastics-Special for PA and PBT	6 or 12	575	Polyamide based	2,0

DowAksa İleri Kompozit Malzemeler Sanayi LTD. ŞTİ.

Head Office: Miralay Şefik Bey Sok. Akhan No: 15 34437 Gümüşsuyu - İstanbul / TÜRKİYE
T: +90(212) 251 45 00 • F: +90(212) 249 35 99

Plant: Denizçalı Köyü Yalova - İzmit Yolu Cad. No: 34
77600 Yalova / TURKEY

T: +90 226 353 25 45

www.dowaksa.com • cfsales@dowaksa.com